

Nordic Joist™
Nordic Structures

PR-L274(C)
Revised April 16, 2025

Products: Nordic Structures Prefabricated Wood I-Joists
Nordic Structures, 1100 Avenue des Canadiens-de-Montréal, Suite 100, Montreal, Québec
Canada H3B 2S2
(514) 871-8526
www.nordic.ca

1. Basis of the product report:
 - 2020 National Building Code of Canada (NBC): Clause 1.2.1.1 of Division A and Clauses 4.1, 4.3.1.1, and 9.23.4.2 of Division B
 - CSA O86-19 Engineering Design in Wood
 - ASTM D5055-16 recognized by CSA O86-19
 - PRI-400 CA Performance Standard for Residential I-Joists (Limit States Design)
 - APA Reports T2004P-3, T2004P-21, T2004P-74, T2004P-76, T2005P-30, T2005P-31, T2006P-12, T2006P-13, T2007P-14A, T2007P-76, T2007P-79A, T2007P-81, T2007P-91, T2008P-17, T2010P-20, T2013P-05, T2013P-37, and T2019P-46, and other qualification data
2. Product description:

Nordic Joist™ Series I-joists, as described in Table 1, are made with lumber flanges and OSB webs in accordance with the in-plant manufacturing standard approved by APA. The Nordic Joist Series are also qualified for PRI-400 Joist Series as shown in Table 1.
3. Design properties:

Tables 2 and 3 list the factored resistances for Nordic Joist Series I-joists. The maximum spans shall be in accordance with the recommendations provided by the manufacturer (www.nordic.ca/en/documentation/technical-documents) and APA PRI-400 CA Performance Standard for Residential I-Joists (Limit States Design) (www.apawood.org/resource-library) for products contained in the PRI Series.
4. Product installation:

Nordic Joist Series I-joists shall be installed in accordance with the recommendations provided by the manufacturer (see link above) and APA Design & Construction Guide, *Performance Rated I-Joist Roof Framing Details*, Form D710 (see link above). Permissible web holes, web stiffeners and cantilever reinforcements shall be in accordance with the recommendations provided by the manufacturer and APA D710 for products contained in the PRI Series.
5. Fire-rated assemblies:

Fire-rated assemblies shall be constructed in accordance with the recommendations provided by the manufacturer (see link above), APA Product Report PR-S274 (see link above), Table 9.10.3.1.-B of NBC, or APA Design & Construction Guide, *Fire-Rated Systems*, Form W305 (see link above) for products contained in the PRI Series.
6. Limitations:
 - a) Nordic Joist Series I-joists shall be designed in accordance with the code using the design properties specified in this report.
 - b) Nordic Joist Series I-joists are limited to dry service conditions as defined in CSA O86, at which the average equilibrium moisture content of solid-sawn lumber over a year is 15% or less and does not exceed 19%.

- c) Nordic Joist Series I-joists are produced at the Nordic Structures facility in Chibougamau, Québec under a quality assurance program audited by APA.
- d) This report is subject to re-examination in one year.

7. Identification:

The Nordic Joist Series I-joists described in this report are identified by a label bearing the manufacturer's name (Nordic Structures) and/or trademark, the APA assigned plant number (1052), the I-joist series, the APA logo, the report number PR-L274 or PR-L274(C), and a means of identifying the date of manufacture.

Table 1. Description of Nordic Joist Series I-Joists^(a)

Joist Series	Joist Depths, mm (in.)	Flanges				Web	
		Material	G ^(b)	Dimension		Material	Thick-ness, mm (in.)
				Depth, mm (in.)	Width, mm (in.)		
NI-20	235 – 302 (9-1/4 – 11-7/8)	Proprietary SPF	0.42	38 (1-1/2)	64 (2-1/2)	OSB	9.5 (3/8)
NI-40	241 – 406 (9-1/2 – 16)	Proprietary SPF	0.42	38 (1-1/2)	64 (2-1/2)	OSB	9.5 (3/8)
NI-40x	200 - 406 (7-7/8 – 16)	Proprietary SPF	0.42	38 (1-1/2)	64 (2-1/2)	OSB	9.5 (3/8)
NI-60	200 – 457 (7-7/8 – 18)	MSR SPF	0.46	38 (1-1/2)	64 (2-1/2)	OSB	9.5 (3/8)
NI-70	241 – 406 (9-1/2 – 16)	MSR SPF	0.42	38 (1-1/2)	89 (3-1/2)	OSB	9.5 (3/8)
NI-80	200 – 406 (7-7/8 – 16)	MSR SPF	0.46	38 (1-1/2)	89 (3-1/2)	OSB	9.5 (3/8)
NI-80x	457 – 610 (18 – 24)	MSR SPF	0.46	38 (1-1/2)	89 (3-1/2)	OSB	11 (7/16)
NI-90	302 – 406 (11-7/8 – 16)	Proprietary SPF	0.50	38 (1-1/2)	89 (3-1/2)	OSB	11 (7/16)
NI-90x	302 – 406 (11-7/8 – 16)	Proprietary SPF	0.42	51 (2)	89 (3-1/2)	OSB	11 (7/16)

^(a) Referenced dimensions are nominal. Tolerances are as specified in the in-plant quality manual.

^(b) Relative density of flanges for use in diaphragm design based on oven-dry weight and oven-dry volume.

Table 2. Factored Resistances for Nordic Joist Series I-Joists^(a)

Joist Depth, mm (in.)	Joist Series	Permitted to Be Labelled As	EI ^(b) (10 ⁶ kN-mm ²)	M _r ^(c) (kN-mm)	V _r ^(d) (kN)	VLC _r ^(e) (kN/m)	K ^(f) (kN)
200 (7-7/8)	NI-40x		396	5,210	6.18	42.3	18,240
	NI-60		422	6,835	6.18	42.3	18,240
	NI-80		585	9,665	6.18	42.3	18,240
235 (9-1/4)	NI-20		396	5,660	7.58	42.3	21,400
	NI-40x		568	6,335	8.21	42.3	21,400
	NI-60		623	8,300	8.21	42.3	21,400
	NI-80		872	11,760	8.21	42.3	21,400
241 (9-1/2)	NI-20	PRI-20	416	5,840	7.86	42.3	21,970
	NI-40	PRI-40 or BLI 40	554	6,165	8.43	42.3	21,970
	NI-40x	PRI-40 or BLI 40	626	6,540	8.43	42.3	21,970
	NI-60	PRI-60	663	8,590	8.43	42.3	21,970
	NI-70		872	11,545	8.43	42.3	21,970
	NI-80		930	12,145	8.43	42.3	21,970
286 (11-1/4)	NI-20		637	7,115	9.41	42.3	26,020
	NI-40x		898	7,970	9.90	42.3	26,020
	NI-60		996	10,440	9.90	42.3	26,020
	NI-80		1,389	14,795	9.90	42.3	26,020
302 (11-7/8)	NI-20	PRI-20	726	7,565	9.97	42.3	27,490
	NI-40	PRI-40 or BLI 40	947	7,995	10.39	42.3	27,490
	NI-40x	PRI-40 or BLI 40	1,065	8,480	10.39	42.3	27,490
	NI-60	PRI-60 or BLI 60	1,136	11,130	11.02	42.3	27,490
	NI-70	PRI-70	1,478	14,960	11.16	42.3	27,490
	NI-80	PRI-80 or BLI 80	1,570	15,740	11.16	42.3	27,490
	NI-90	PRI-90	1,725	19,800	13.52	42.3	27,490
	NI-90x		1,765	21,345	14.43	42.3	27,490
356 (14)	NI-40	PRI-40 or BLI 40	1,383	9,630	12.29	42.3	32,380
	NI-40x	PRI-40 or BLI 40	1,550	10,215	12.29	42.3	32,380
	NI-60	PRI-60 or BLI 60	1,676	13,405	12.29	42.3	32,380
	NI-70	PRI-70	2,149	18,015	12.74	42.3	32,380
	NI-80	PRI-80 or BLI 80	2,302	18,955	12.88	42.3	32,380
	NI-90	PRI-90	2,517	23,835	14.92	42.3	32,380
	NI-90x		2,612	25,740	15.52	42.3	32,380
406 (16)	NI-40	PRI-40 or BLI 40	1,885	11,160	14.04	42.3	37,010
	NI-40x	PRI-40 or BLI 40	2,106	11,840	14.04	42.3	37,010
	NI-60	PRI-60 or BLI 60	2,293	15,550	14.04	42.3	37,010
	NI-70	PRI-70	2,913	20,895	14.04	42.3	37,010
	NI-80	PRI-80 or BLI 80	3,134	21,975	14.53	42.3	37,010
	NI-90	PRI-90	3,406	27,645	16.36	42.3	37,010
	NI-90x		3,573	29,540	16.36	42.3	37,010
457 (18)	NI-60		2,924	17,590	14.04	39.1	41,640
	NI-80x		4,015	24,780	16.57	27.0	41,640
508 (20)	NI-80x		5,082	27,770	17.20	27.0	46,260
559 (22)	NI-80x		6,288	30,770	17.76	27.0	50,890
610 (24)	NI-80x		7,634	33,770	18.26	27.0	55,510

For Imperial: 1 mm = 0.0394 in., 1 N = 0.2248 lbf, 1 kN/m = 5.71 lbf/in.

- (a) All factored resistance values include the resistance factor specified in CSA O86. The tabulated values are for the standard term of load duration ($K_D = 1.0$). All values, except for EI, vertical load resistance, and K, are permitted to be adjusted for other load durations as permitted by the code.
- (b) Bending stiffness (EI) of the I-joist.
- (c) Factored moment resistance (M_r) of the I-joist.
- (d) Factored shear resistance (V_r) of the I-joist.
- (e) Factored uniform vertical load resistance (VLC_r) of the I-joist.

- (f) Coefficient of shear deflection (K). For calculating uniform load and center-point load deflections of the I-joist in a simple-span application, use Equations 1 and 2.

$$\text{Uniform Load:} \quad \delta = \frac{5 \omega L^4}{384 EI} + \frac{\omega L^2}{K} \quad [1]$$

$$\text{Center-Point Load:} \quad \delta = \frac{PL^3}{48 EI} + \frac{2 PL}{K} \quad [2]$$

where δ = calculated deflection (mm), ω = uniform load (kN/mm),
P = concentrated load (kN), L = design span (mm),
EI = bending stiffness of the I-joist (kN-mm²), and K = coefficient of shear deflection (kN).

Table 3. Factored Reaction Resistances for Nordic Joist Series I-Joists^(a,b,c,d)

Joist Depth mm (in.)	Joist Series	Permitted to Be Labelled As	Intermediate Reaction (kN)				End Reaction (kN)					
			89 mm (3-1/2 in.) Brg. Length		140 mm (5-1/2 in.) Brg. Length		38 mm (1-1/2 in.) Brg. Length		45 mm (1-3/4 in.) Brg. Length		102 mm (4 in.) Brg. Length	
			Brg. Stiffeners		Brg. Stiffeners		Brg. Stiffeners		Brg. Stiffeners		Brg. Stiffeners	
			No	Yes	No	Yes	No	Yes	No	Yes	No	Yes
200 (7-7/8)	NI-40x		14.11	14.11	14.11	14.11	NA	NA	6.18	6.18	6.18	6.18
	NI-60		14.11	14.11	14.11	14.11	NA	NA	6.18	6.18	6.18	6.18
	NI-80		14.11	14.11	14.11	14.11	NA	NA	6.18	6.18	6.18	6.18
235 (9-1/4)	NI-20		16.50	16.57	17.62	17.62	NA	NA	7.13	7.13	7.58	7.58
	NI-40x		16.50	16.57	17.80	17.90	NA	NA	7.97	7.97	8.21	8.21
	NI-60		16.50	16.67	17.83	17.90	NA	NA	7.97	7.97	8.21	8.21
241 (9-1/2)	NI-80		16.50	18.04	18.11	18.11	NA	NA	8.21	8.21	8.21	8.21
	NI-20	PRI-20	16.92	17.03	18.08	18.08	7.27	7.27	7.27	7.27	7.86	7.86
	NI-40	PRI-40 or BLI 40	16.92	17.03	18.46	18.57	7.44	8.42	8.25	8.42	8.42	8.42
241 (9-1/2)	NI-40x	PRI-40 or BLI 40	16.92	17.03	18.46	18.57	7.44	8.42	8.25	8.42	8.42	8.42
	NI-60	PRI-60	16.96	17.13	18.50	18.71	7.44	8.42	8.25	8.42	8.42	8.42
	NI-70		16.96	18.75	18.85	18.85	7.44	8.42	8.42	8.42	8.42	8.42
241 (9-1/2)	NI-80		16.96	18.75	18.85	18.85	7.44	8.42	8.42	8.42	8.42	8.42
	NI-20		19.97	20.15	21.38	21.38	7.37	7.37	8.35	8.35	9.41	9.41
	NI-40x		19.97	20.15	23.17	23.38	7.76	9.90	8.78	9.90	9.90	9.90
286 (11-1/4)	NI-60		20.01	20.40	23.24	23.70	7.76	9.90	8.78	9.90	9.90	9.90
	NI-80		20.01	22.15	23.94	23.94	7.76	9.90	9.34	9.90	9.90	9.90
	NI-20	PRI-20	21.06	21.27	22.57	22.57	7.41	7.41	8.74	8.74	9.97	9.97
302 (11-7/8)	NI-40	PRI-40 or BLI 40	21.06	21.27	24.85	25.10	7.90	9.34	8.95	10.39	10.39	10.39
	NI-40x	PRI-40 or BLI 40	21.06	21.27	24.85	25.10	7.90	9.34	8.95	10.39	10.39	10.39
	NI-60	PRI-60 or BLI 60	21.10	21.55	24.92	25.45	7.90	9.34	8.95	10.39	10.88	11.02
302 (11-7/8)	NI-70	PRI-70	21.10	23.38	25.77	25.77	7.90	9.34	9.48	10.39	10.88	11.16
	NI-80	PRI-80 or BLI-80	21.10	23.38	25.77	25.77	7.90	9.34	9.48	11.16	10.88	11.16
	NI-90	PRI-90	23.55	23.55	25.77	25.77	7.90	9.34	9.83	10.39	13.23	13.52
302 (11-7/8)	NI-90x		29.28	29.28	29.28	29.28	7.90	9.34	12.39	14.43	13.23	14.43
	NI-40	PRI-40 or BLI 40	21.98	22.19	24.78	25.03	8.28	11.69	9.30	11.87	10.88	12.29
	NI-40x	PRI-40 or BLI 40	21.98	22.19	24.78	25.03	8.28	11.69	9.30	11.87	10.88	12.29
356 (14)	NI-60	PRI-60 or BLI 60	22.05	22.89	24.85	26.64	8.28	11.69	9.44	11.87	10.88	12.29
	NI-70	PRI-70	23.38	25.56	26.82	28.61	8.28	11.69	10.22	11.87	10.88	12.74
	NI-80	PRI-80 or BLI 80	23.38	25.56	26.82	28.61	8.28	11.69	10.22	12.36	11.23	12.88
356 (14)	NI-90	PRI-90	23.55	25.56	26.82	28.61	8.28	11.69	10.22	11.87	13.23	14.92
	NI-90x		29.28	29.28	29.28	29.28	8.28	11.69	12.64	15.52	13.23	15.52

(Footnotes on the following page)

Table 3. Factored Reaction Resistances for Nordic Joist Series I-Joists^(a,b,c,d) (Continued)

Joist Depth mm (in.)	Joist Series	Permitted to Be Labelled As	Intermediate Reaction (kN)				End Reaction (kN)					
			89 mm (3-1/2 in.) Brg. Length		140 mm (5-1/2 in.) Brg. Length		38 mm (1-1/2 in.) Brg. Length		45 mm (1-3/4 in.) Brg. Length		102 mm (4 in.) Brg. Length	
			Brg. Stiffeners		Brg. Stiffeners		Brg. Stiffeners		Brg. Stiffeners		Brg. Stiffeners	
			No	Yes	No	Yes	No	Yes	No	Yes	No	Yes
406 (16)	NI-40	PRI-40 or BLI-40	22.85	23.06	24.71	25.24	NA	NA	9.62	13.16	10.88	14.04
	NI-40x	PRI-40 or BLI-40	22.85	23.06	24.71	25.24	NA	NA	9.62	13.16	10.88	14.04
	NI-60	PRI-60 or BLI 60	22.92	24.15	24.78	27.77	NA	NA	9.90	13.16	10.88	14.04
	NI-70	PRI-70	25.56	27.59	27.80	31.28	NA	NA	10.88	13.16	10.88	14.04
	NI-80	PRI-80 or BLI 80	25.56	27.59	27.80	31.28	NA	NA	10.88	13.44	11.23	14.53
	NI-90	PRI-90	25.56	27.59	27.80	31.28	NA	NA	10.88	13.16	13.23	16.36
457 (18)	NI-60		19.66	25.42	22.89	28.89	NA	NA	10.36	14.04	12.99	14.04
	NI-80x		21.87	26.82	23.03	31.03	NA	NA	9.13	13.34	12.99	16.57
508 (20)	NI-80x		22.40	28.93	23.94	32.12	NA	NA	9.27	14.36	13.34	17.20
559 (22)	NI-80x		22.92	31.07	24.82	33.21	NA	NA	9.41	15.41	13.69	17.76
610 (24)	NI-80x		23.45	33.17	25.73	34.30	NA	NA	9.55	16.43	14.04	18.25

For Imperial: 1 mm = 0.0394 in., 1 N = 0.2248 lbf

- (a) The tabulated end and intermediate reaction values shall not be greater than the bearing capacity of the flanges based on the specified compressive strength perpendicular to grain of 5.3 MPa when determined in accordance with CSA O86. Consult with the manufacturer for the factored compressive strength perpendicular to the grain of the flange for bearing design.
- (b) Factored reaction resistance is for the standard term of load duration ($K_D = 1.0$) and shall be permitted to be adjusted for other load durations as permitted by the code.
- (c) Factored reaction resistance shall be permitted to be increased over that tabulated for the minimum bearing length by linear interpolation of the reaction resistance between the minimum and maximum bearing lengths. Extrapolation beyond the minimum and maximum bearing lengths is beyond the scope of this table.
- (d) Web stiffeners, when required, shall be installed in accordance with Table 4 and the recommendations provided by the manufacturer.

Table 4. Minimum Dimensions for Web Stiffeners^(a)

Joist Series	Web Stiffeners		Flange Width, b _f , mm (in.)
	Thickness, mm (in.)	Width, mm (in.)	
NI-20	25 (1)	59 (2-5/16)	64 (2-1/2)
NI-40	25 (1)	59 (2-5/16)	64 (2-1/2)
NI-40x	25 (1)	59 (2-5/16)	64 (2-1/2)
NI-60	25 (1)	59 (2-5/16)	64 (2-1/2)
NI-70	38 (1-1/2)	59 (2-5/16)	89 (3-1/2)
NI-80	38 (1-1/2)	59 (2-5/16)	89 (3-1/2)
NI-80x	38 (1-1/2)	59 (2-5/16)	89 (3-1/2)
NI-90	38 (1-1/2)	59 (2-5/16)	89 (3-1/2)
NI-90x	38 (1-1/2)	59 (2-5/16)	89 (3-1/2)

^(a) Web stiffener length is 3 mm (1/8 inch) to 6 mm (1/4 inch) less than the clear distance between flanges. Stiffeners 25 mm (1-inch) thick are wood structural panels and stiffeners 38 mm (1-1/2-inch) thick are SPF lumber (relative density of 0.42) or denser lumber.

APA – *The Engineered Wood Association* is an approved national standards developer accredited by American National Standards Institute (ANSI). APA publishes ANSI standards and Voluntary Product Standards for wood structural panels and engineered wood products. APA is an accredited certification body under ISO/IEC 17065 by Standards Council of Canada (SCC), an accredited inspection agency under ISO/IEC 17020 by ANSI National Accreditation Board (ANAB), and an accredited testing organization under ISO/IEC 17025 by ANAB. APA is also an approved Product Certification Agency, Testing Laboratory, Quality Assurance Entity, and Validation Entity by the State of Florida, and an approved testing laboratory by City of Los Angeles.

**APA – THE ENGINEERED WOOD ASSOCIATION
 HEADQUARTERS**

7011 So. 19th St. • Tacoma, Washington 98466
 Phone: (253) 565-6600 • Fax: (253) 565-7265 • Internet Address: www.apawood.org

PRODUCT SUPPORT HELP DESK
 (253) 620-7400 • E-mail Address: help@apawood.org

DISCLAIMER

APA Product Report® is a trademark of APA – *The Engineered Wood Association*, Tacoma, Washington. The information contained herein is based on the product evaluation in accordance with the references noted in this report. No warranties, express or implied, including as to fitness for a particular purpose, are made regarding this report. Neither APA nor its members shall be liable, or assume any legal liability or responsibility, for damages, direct or indirect, arising from the use, application of, and/or reference to opinions, findings, conclusions or recommendations included in this report. Consult your local jurisdiction or design professional to assure compliance with code, construction, and performance requirements. Because APA has no control over quality of workmanship or the conditions under which engineered wood products are used, it cannot accept responsibility for product performance or designs as actually constructed.