

## **Nordic X-Lam Nordic Structures**

**PR-L306C**

Revised September 5, 2018

Products: Nordic X-Lam  
Nordic Structures  
1100 Avenue des Canadiens-de-Montréal, Suite 504  
Montreal, Québec, Canada H3B 2S2  
(514) 871-8526  
[www.nordic.ca](http://www.nordic.ca)

1. Basis of the product report:
  - 2015 National Building Code of Canada (NBC): Clause 1.2.1.1 of Division A and Clauses 4.1, 4.3.1.1, and 9.23 of Division B
  - CAN/CSA O86-14 (reprint 2016) Engineering Design in Wood
  - ANSI/APA PRG 320-2017 Performance Rated Cross-Laminated Timber
  - FPInnovations Reports 201002775, 201004981, 301010401, 301010956, and 301011903, and other qualification data
2. Product description:

Nordic X-Lam cross-laminated timber (CLT) is manufactured with spruce-pine-fir in accordance with the E1 or custom layups of ANSI/APA PRG 320 through product qualification and/or mathematical models using principles of engineering mechanics. Nordic X-Lam can be used in floor, roof, and wall applications, and is manufactured in a plank billet with nominal widths of 305 to 2438 mm (12 to 96 inches), thicknesses of 76 to 381 mm (3 to 15 inches), and lengths up to 19.5 m (64 feet).
3. Design properties:

Nordic X-Lam CLT shall be designed with the design properties and capacities provided in Tables 1, 2, and 3, or with the maximum load table provided by the manufacturer ([www.nordic.ca/en/documentation/technical-documents](http://www.nordic.ca/en/documentation/technical-documents)). The design adjustment factors, shall be based on CSA O86, the recommendations provided by the manufacturer, or the 2011 Canadian CLT Handbook ([www.fpinnovations.ca/Pages/CLTForm.aspx](http://www.fpinnovations.ca/Pages/CLTForm.aspx)), and approved by the engineer of record. The lateral resistance of Nordic X-Lam CLT, when used as shearwalls or diaphragms, depends on the panel-to-panel connection and anchorage designs, and shall be consulted with the CLT manufacturer and approved by the engineer of record.
4. Product installation:

Nordic X-Lam CLT shall be installed in accordance with the recommendations provided by the manufacturer (see link above) and the engineering drawing approved by the engineer of record. Permissible details shall be in accordance with the engineering drawing.
5. Fire-rated assemblies:

Fire-rated assemblies shall be constructed in accordance with the recommendations provided by the manufacturer (see link above). Procedures specified in Annex B of CSA O86 or Chapter 8 of the 2011 Canadian CLT Handbook (see link above) may be used in the fire design of Nordic X-Lam CLT when approved by the authority having jurisdiction.

Nordic X-Lam CLT has been tested in accordance with CAN/ULC S102-10, and meets the flame-spread rating of 26 – 75 and smoke developed classification of 0 – 450.

6. Limitations:
  - a) Nordic X-Lam CLT shall be designed in accordance with principles of mechanics using the design properties specified in this report or provided by the manufacturer.
  - b) Nordic X-Lam products shall be limited to dry service conditions where the average equilibrium moisture content of solid-sawn lumber over a year is 15 percent or less and does not exceed 19 percent.
  - c) Design properties for Nordic X-Lam CLT, when used as beams or lintels with loads applied parallel to the face-bond gluelines, are beyond the scope of this report.
  - d) Nordic X-Lam CLT shall be manufactured in accordance with layup combinations specified in ANSI/APA PRG 320 or proprietary Nordic X-Lam CLT manufacturing specifications documented in the in-plant manufacturing standard approved by APA.
  - e) Nordic X-Lam CLT is produced at the Nordic Structures, Chibougamau, Quebec facilities under a quality assurance program audited by APA.
  - f) This report is subject to re-examination in one year.
  
7. Identification:

Nordic X-Lam CLT described in this report is identified by a label bearing the manufacturer's name (Nordic Structures) and/or trademark, the APA assigned plant number (1112), the product standard (ANSI/APA PRG 320), the APA logo, the CLT layup (E1), the report number PR-L306, and a means of identifying the date of manufacture.

Table 1. LSD Specified Strengths and Modulus of Elasticity<sup>(a)</sup> for Lumber Laminations Used in Nordic X-Lam (For Use in Canada)

CLT Layup	Lumber Laminations Used in Major Strength Direction						Lumber Laminations Used in Minor Strength Direction					
	f <sub>b</sub> (MPa)	E (MPa)	f <sub>t</sub> (MPa)	f <sub>c</sub> (MPa)	f <sub>v</sub> (MPa)	f <sub>s</sub> (MPa)	f <sub>b</sub> (MPa)	E (MPa)	f <sub>t</sub> (MPa)	f <sub>c</sub> (MPa)	f <sub>v</sub> (MPa)	f <sub>s</sub> (MPa)
E1	28.2	11,700	15.4	19.3	1.5	0.5	7.0	9,000	3.2	9.0	1.5	0.5

For Imperial: 1 MPa = 145.04 psi

<sup>(a)</sup> Tabulated values are Limit States design values and not permitted to be increased for the lumber size adjustment factor in accordance with CSA O86. The design values shall be used in conjunction with the section properties provided by the CLT manufacturer based on the actual layup used in manufacturing the CLT panel (see Table 2).

Table 2. LSD Stiffness and Unfactored Resistance Values<sup>(a)</sup> for Nordic X-Lam Listed in Table 1 (For Use in Canada)

CLT Layup <sup>(b)</sup>	Layup ID <sup>(c)</sup>	Thick-ness, t <sub>p</sub> (mm)	Lamination Thickness (mm) in CLT Layup						Major Strength Direction					Minor Strength Direction					
			=	⊥	=	⊥	=	⊥	=	(f <sub>b</sub> S) <sub>eff,f,0</sub> (10 <sup>6</sup> N-mm/m)	(EI) <sub>eff,f,0</sub> (10 <sup>9</sup> N-mm <sup>2</sup> /m)	(GA) <sub>eff,f,0</sub> (10 <sup>6</sup> N/m)	V <sub>s,0</sub> (kN/m)	G <sub>e,0</sub> t <sub>p</sub> <sup>(d)</sup> (10 <sup>6</sup> N/m)	(f <sub>b</sub> S) <sub>eff,f,90</sub> (10 <sup>6</sup> N-mm/m)	(EI) <sub>eff,f,90</sub> (10 <sup>9</sup> N-mm <sup>2</sup> /m)	(GA) <sub>eff,f,90</sub> (10 <sup>6</sup> N/m)	V <sub>s,90</sub> (kN/m)	G <sub>e,90</sub> t <sub>p</sub> <sup>(d)</sup> (10 <sup>6</sup> N/m)
E1	78-3s	78	25.8	26.8	25.8				24	452	5.4	26	20	0.84	14	6.9	8.9	20	
	89-3s	89	34.9	19.1	34.9				31	678	7.5	30	22	0.42	5.2	5.7	6.3	22	
	105-3s	105	34.9	34.9	34.9				42	1,081	7.3	35	26	1.40	32	9.0	12	26	
	131-5s	131	25.8	26.8	25.8	26.8	25.8		54	1,735	11	44	33	7.1	364	14	26	33	
	140-4s	140	34.9	2 x 34.9	34.9				68	2,334	8.5	47	35	5.7	256	18	23	35	
	143-5s	143	34.9	19.1	34.9	19.1	34.9		72	2,514	15	48	36	5.6	261	11	24	36	
	175-5s	175	34.9	34.9	34.9	34.9	34.9		97	4,140	15	58	44	12	832	18	35	44	
	197-7s	197	34.9	19.1	34.9	19.1	34.9	19.1	34.9	128	6,152	23	66	49	13	1,037	17	42	49
	213-7I	213	2 x 34.9	19.1	34.9	19.1	2 x 34.9			174	9,056	25	71	53	5.6	261	14	24	53
	220-7s	220	34.9	26.8	34.9	26.8	34.9	26.8	34.9	149	8,019	22	73	55	20	1,913	22	50	55
	244-7s	244	34.9	34.9	34.9	34.9	34.9	34.9	34.9	172	10,240	22	81	61	28	3,199	27	58	61
	244-7I	244	2 x 34.9	34.9	34.9	34.9	2 x 34.9			221	13,194	22	81	61	12	832	20	35	61
	267-9I	267	2 x 34.9	19.1	34.9	19.1	34.9	19.1	2 x 34.9	264	17,211	32	89	67	13	1,037	19	42	67
	314-9I	314	2 x 34.9	34.9	34.9	34.9	34.9	34.9	2 x 34.9	342	26,272	29	105	79	28	3,199	29	58	79

For Imperial: 1 mm = 0.0394 in.; 1 m = 3.28 ft; 1 N = 0.2248 lbf

<sup>(a)</sup> Tabulated values are unfactored Limit States design values and not permitted to be increased for the lumber size adjustment factor in accordance with CSA O86.

<sup>(b)</sup> The CLT layups are developed based on ANSI/APA PRG 320, as permitted by the standard.

<sup>(c)</sup> The layup designation refers to the panel thickness (in mm), the number of layers, and the layup combination ("s" for standard perpendicular layers, and "I" for doubled outermost parallel layers).

<sup>(d)</sup> G<sub>e,0</sub> and G<sub>e,90</sub> = 250 MPa based on product performance testing.

Table 3. LSD Specified In-Plane Shear Strength for Nordic X-Lam<sup>(a)</sup> (For Use in Canada)

CLT Layup	Layup ID	Thickness, $t_p$ (mm)	Specified In-Plane Shear Strength	
			$f_{v,e,0}$ (MPa)	$f_{v,e,90}$ (MPa)
E1	78-3s	78	2.0 <sup>(b)</sup>	2.4 <sup>(b)</sup>
	89-3s	89	2.0	2.4 <sup>(b)</sup>
	105-3s	105	2.0	2.4
	131-5s	131	2.4 <sup>(c)</sup>	2.7 <sup>(c)</sup>
	140-4s	140	1.8	2.4 <sup>(b)</sup>
	143-5s	143	2.4 <sup>(c)</sup>	2.7 <sup>(c)</sup>
	175-5s	175	2.4	2.7
	197-7s	197	2.0 <sup>(b)</sup>	2.7 <sup>(c)</sup>
	213-7l	213	2.4 <sup>(c)</sup>	2.7 <sup>(c)</sup>
	220-7s	220	2.4 <sup>(c)</sup>	2.7 <sup>(c)</sup>
	244-7s	244	2.4 <sup>(c)</sup>	2.7 <sup>(c)</sup>
	244-7l	244	2.4 <sup>(c)</sup>	2.7 <sup>(c)</sup>
	267-9l	267	2.0 <sup>(b)</sup>	2.7 <sup>(c)</sup>
314-9l	314	2.4 <sup>(c)</sup>	2.7 <sup>(c)</sup>	

For Imperial: 1 MPa = 145.04 psi

- (a) The tabulated values are for Limit States Design (LSD) for use in Canada based on the full CLT thickness in the major strength direction ( $f_{v,e,0}$ ) and minor strength direction ( $f_{v,e,90}$ ). The values shall be used in conjunction with the CLT thickness,  $t_p$ , to determine the in-plane shear capacities. If the net CLT thickness is less than the full CLT thickness, the in-plane shear capacities shall be calculated based on the net CLT thickness.
- (b) Based on test results from 105-3s.
- (c) Based on test results from 175-5s.

APA – The Engineered Wood Association is an approved national standards developer accredited by American National Standards Institute (ANSI). APA publishes ANSI standards and Voluntary Product Standards for wood structural panels and engineered wood products. APA is an accredited certification body under ISO/IEC 17065 by Standards Council of Canada (SCC), an accredited inspection agency under ISO/IEC 17020 by International Code Council (ICC) International Accreditation Service (IAS), and an accredited testing organization under ISO/IEC 17025 by IAS. APA is also an approved Product Certification Agency, Testing Laboratory, Quality Assurance Entity, and Validation Entity by the State of Florida, and an approved testing laboratory by City of Los Angeles.

**APA – THE ENGINEERED WOOD ASSOCIATION  
 HEADQUARTERS**

7011 So. 19<sup>th</sup> St. ▪ Tacoma, Washington 98466  
 Phone: (253) 565-6600 ▪ Fax: (253) 565-7265 ▪ Internet Address: [www.apawood.org](http://www.apawood.org)

**PRODUCT SUPPORT HELP DESK**  
 (253) 620-7400 ▪ E-mail Address: [help@apawood.org](mailto:help@apawood.org)

**DISCLAIMER**

APA Product Report® is a trademark of APA – The Engineered Wood Association, Tacoma, Washington. The information contained herein is based on the product evaluation in accordance with the references noted in this report. Neither APA, nor its members make any warranty, expressed or implied, or assume any legal liability or responsibility for the use, application of, and/or reference to opinions, findings, conclusions, or recommendations included in this report. Consult your local jurisdiction or design professional to assure compliance with code, construction, and performance requirements. Because APA has no control over quality of workmanship or the conditions under which engineered wood products are used, it cannot accept responsibility for product performance or designs as actually constructed.