

Nordic X-Lam
Nordic Structures

PR-L306C
Revised April 9, 2021

Products: Nordic X-Lam

Nordic Structures, 1100 Avenue des Canadiens-de-Montréal, Suite 100, Montreal, Québec
Canada H3B 2S2

(514) 871-8526

www.nordic.ca

1. Basis of the product report:
 - 2015 National Building Code of Canada (NBC): Clause 1.2.1.1 of Division A and Clauses 4.1, 4.3.1.1, and 9.23 of Division B
 - CAN/CSA O86-19 Engineering Design in Wood
 - ANSI/APA PRG 320-2019 Standard for Performance-Rated Cross-Laminated Timber
 - ANSI/APA PRG 320-2018 recognized by CSA O86-19
 - FPInnovations Reports 201002775, 201004981, 301010401, 301010956, and 301011903, and other qualification data
2. Product description:

Nordic X-Lam cross-laminated timber (CLT) is manufactured with Spruce-Pine-Fir (mainly Black Spruce) lumber in accordance with the E1 or custom layouts of ANSI/APA PRG 320 through product qualification and/or mathematical models using principles of engineering mechanics. Nordic X-Lam can be used in floor, roof, and wall applications, and is manufactured in a plank billet with nominal widths of 305 to 2,700 mm (12 to 106-1/4 inches), thicknesses of 76 to 381 mm (3 to 15 inches), and lengths up to 19.5 m (64 feet).
3. Design properties:

Nordic X-Lam CLT shall be designed with the design properties and capacities provided in Tables 1, 2, and 3, or with the maximum load table provided by the manufacturer (www.nordic.ca/en/documentation/technical-documents). Note that the unbalanced layout listed in Tables 2 and 3, E1/140-4I, shall be stamped with the word "TOP" on the side that contains a single outermost layer in the major strength direction. The design adjustment factors, shall be based on CSA O86, the recommendations provided by the manufacturer, or the 2019 Canadian CLT Handbook (<https://web.fpinnovations.ca/clt/>), and approved by the engineer of record. The lateral resistance of Nordic X-Lam CLT, when used as shearwalls or diaphragms, depends on the panel-to-panel connection and anchorage designs, and shall be designed in accordance with Clause 11.9 of CSA O86 or consulted with the CLT manufacturer and approved by the engineer of record.
4. Product installation:

Nordic X-Lam CLT shall be installed in accordance with the recommendations provided by the manufacturer (see link above) and the engineering drawing approved by the engineer of record. Permissible details shall be in accordance with the engineering drawing.
5. Fire-rated assemblies:

Fire-rated assemblies shall be constructed in accordance with the recommendations provided by the manufacturer (see link above). Procedures specified in Annex B of CSA O86 or Chapter 8 of the 2019 Canadian CLT Handbook (see link above) may be used in the fire design of Nordic X-Lam CLT when approved by the authority having jurisdiction.

Nordic X-Lam CLT has been tested in accordance with CAN/ULC S102-10, and meets the flame-spread rating of 26 – 75 and smoke developed classification of 0 – 450.

6. Limitations:
 - a) Nordic X-Lam CLT shall be designed in accordance with principles of mechanics using the design properties specified in this report or provided by the manufacturer.
 - b) Nordic X-Lam products shall be limited to dry service conditions where the average equilibrium moisture content of solid-sawn lumber over a year is 15 percent or less and does not exceed 19 percent.
 - c) Design properties for Nordic X-Lam CLT, when used as beams or lintels with loads applied parallel to the face-bond gluelines, other than the edgewise shear properties (see Table 3), are beyond the scope of this report.
 - d) Nordic X-Lam CLT shall be manufactured in accordance with layup combinations specified in ANSI/APA PRG 320 or custom Nordic X-Lam CLT manufacturing specifications documented in the in-plant manufacturing standard approved by APA.
 - e) Nordic X-Lam CLT is produced at the Nordic Structures, Chibougamau, Quebec facilities under a quality assurance program audited by APA.
 - f) This report is subject to re-examination in one year.

7. Identification:

Nordic X-Lam CLT described in this report is identified by a label bearing the manufacturer's name (Nordic Structures) and/or trademark, the APA assigned plant number (1112), the product standard (ANSI/APA PRG 320), the APA logo, the CLT grade (E1), the report number PR-L306, and a means of identifying the date of manufacture.

Table 1. LSD Specified Strength and Modulus of Elasticity^(a) for Lumber Laminations Used in Nordic X-Lam (for Use in Canada)

CLT Grade	Lumber Laminations Used in Major Strength Direction								Lumber Laminations Used in Minor Strength Direction							
	Grade & Species	f _b (MPa)	E (MPa)	f _t (MPa)	f _c (MPa)	f _{c⊥} (MPa)	f _v (MPa)	f _s (MPa)	Grade & Species	f _b (MPa)	E (MPa)	f _t (MPa)	f _c (MPa)	f _{c⊥} (MPa)	f _v (MPa)	f _s (MPa)
E1	1950f-1.7E SPF	28.2	11,700	15.4	19.3	5.3	1.5	0.50	No. 3 SPF	7.0	9,000	3.2	9.0	5.3	1.5	0.50

For Imperial: 1 MPa = 145.04 psi

^(a) Tabulated values are Limit States design values and not permitted to be increased for the lumber size adjustment factor in accordance with CSA O86. The design values shall be used in conjunction with the section properties provided by the CLT manufacturer based on the actual layout used in manufacturing the CLT panel (see Table 2).

Table 2. LSD Flatwise Bending Stiffness and Unfactored Resistance Values^(a) for Nordic X-Lam (for Use in Canada)

CLT Grade ^(b)	Layout ID ^(c)	Thick-ness, t _p (mm)	Lamination Thickness (mm) in CLT Layout							Major Strength Direction				Minor Strength Direction			
			=	⊥	=	⊥	=	⊥	=	(f _b S) _{eff,f,0} (10 ⁶ N-mm/m)	(EI) _{eff,f,0} (10 ⁹ N-mm ² /m)	(GA) _{eff,f,0} (10 ⁶ N/m)	V _{s,0} (kN/m)	(f _b S) _{eff,f,90} (10 ⁶ N-mm/m)	(EI) _{eff,f,90} (10 ⁹ N-mm ² /m)	(GA) _{eff,f,90} (10 ⁶ N/m)	V _{s,90} (kN/m)
E1	78-3s	78	25.8	26.8	25.8					24	452	5.4	26	0.84	14	6.9	8.9
	89-3s	89	35	19.1	35					31	683	7.6	30	0.43	5.2	5.7	6.4
	105-3s	105	35	35	35					42	1,088	7.3	35	1.4	32	9.1	12
	131-5s	131	25.8	26.8	25.8	26.8	25.8			54	1,733	11	44	7.1	363	14	26
	140-4s	140	35	2 x 35	35					69	2,350	8.5	47	5.7	257	18	23
	140-4I ^(d)	140	2 x 35	35	35					67	2,473	11	47	1.4	32	9.8	12
	143-5s	143	35	19.1	35	19.1	35			72	2,531	15	48	5.6	263	11	24
	175-5s	175	35	35	35	35	35			98	4,166	15	58	12	837	18	35
	197-7s	197	35	19.1	35	19.1	35	19.1	35	129	6,194	23	66	13	1,045	17	42
	213-7I	213	2 x 35	19.1	35	19.1	2 x 35			175	9,117	25	71	5.6	263	14	24
	220-7s	220	35	26.8	35	26.8	35	26.8	35	150	8,050	22	73	20	1,915	22	50
	245-7s	245	35	35	35	35	35	35	35	172	10,306	22	82	29	3,220	27	58
	245-7I	245	2 x 35	35	35	35	2 x 35			222	13,279	22	82	12	837	20	35
	267-9I	267	2 x 35	19.1	35	19.1	35	19.1	2 x 35	266	17,327	32	89	13	1,045	19	42
	315-9I	315	2 x 35	35	35	35	35	35	2 x 35	344	26,442	29	105	29	3,220	29	58

For Imperial: 1 mm = 0.0394 in.; 1 m = 3.28 ft; 1 N = 0.2248 lbf

^(a) Tabulated values are unfactored Limit States Design (LSD) design values and not permitted to be increased for the lumber size adjustment factor in accordance with CSA O86.

^(b) The CLT layouts are developed based on ANSI/APA PRG 320, as permitted by the standard.

^(c) The layout designation refers to the panel thickness (in mm), the number of layers, and the layout combination ("s" for standard perpendicular layers, and "I" for doubled outermost parallel layers).

^(d) This layout is not balanced (the top and bottom layers are different in the layer thickness). The side that contains a single outermost layer in the major strength direction must be stamped with the word "TOP".

Table 3. LSD Specified Edgewise Shear Strength and Rigidity for Nordic X-Lam (for Use in Canada)

CLT Grade	Layup ID	Thickness, t_p (mm)	Major Strength Direction		Minor Strength Direction	
			$f_{v,e,0}^{(a)}$ (MPa)	$G_{e,0} t_p^{(d)}$ (10^6 N/m)	$f_{v,e,90}^{(a)}$ (MPa)	$G_{e,90} t_p^{(d)}$ (10^6 N/m)
E1	78-3s	78	2.0 ^(b)	20	2.4 ^(b)	20
	89-3s	89	2.0	22	2.4 ^(b)	22
	105-3s	105	2.0	26	2.4	26
	131-5s	131	2.4 ^(c)	33	2.7 ^(c)	33
	140-4s	140	1.8	35	2.4 ^(b)	35
	140-4l	140	2.0 ^(b)	35	2.4 ^(b)	35
	143-5s	143	2.4 ^(c)	36	2.7 ^(c)	36
	175-5s	175	2.4	44	2.7	44
	197-7s	197	2.0 ^(b)	49	2.7 ^(c)	49
	213-7l	213	2.4 ^(c)	53	2.7 ^(c)	53
	220-7s	220	2.4 ^(c)	55	2.7 ^(c)	55
	245-7s	245	2.4 ^(c)	61	2.7 ^(c)	61
	245-7l	245	2.4 ^(c)	61	2.7 ^(c)	61
	267-9l	267	2.0 ^(b)	67	2.7 ^(c)	67
	315-9l	315	2.4 ^(c)	79	2.7 ^(c)	79

For Imperial: 1 MPa = 145.04 psi

- (a) The tabulated values are LSD design values for use in Canada based on the full CLT thickness in the major strength direction ($f_{v,e,0}$) and minor strength direction ($f_{v,e,90}$). The values shall be used in conjunction with the CLT thickness, t_p , to determine the in-plane shear capacities. If the net CLT thickness is less than the full CLT thickness, the in-plane shear capacities shall be calculated based on the net CLT thickness.
- (b) Based on test results from 105-3s.
- (c) Based on test results from 175-5s.
- (d) Edgewise shear rigidity is based on $G_{e,0}$ and $G_{e,90}$ values of 250 MPa and the CLT thickness, t_p , in accordance with product performance testing.

APA – The Engineered Wood Association is an approved national standards developer accredited by American National Standards Institute (ANSI). APA publishes ANSI standards and Voluntary Product Standards for wood structural panels and engineered wood products. APA is an accredited certification body under ISO/IEC 17065 by Standards Council of Canada (SCC), an accredited inspection agency under ISO/IEC 17020 by International Code Council (ICC) International Accreditation Service (IAS), and an accredited testing organization under ISO/IEC 17025 by IAS. APA is also an approved Product Certification Agency, Testing Laboratory, Quality Assurance Entity, and Validation Entity by the State of Florida, and an approved testing laboratory by City of Los Angeles.

**APA – THE ENGINEERED WOOD ASSOCIATION
 HEADQUARTERS**

7011 So. 19th St. ▪ Tacoma, Washington 98466
 Phone: (253) 565-6600 ▪ Fax: (253) 565-7265 ▪ Internet Address: www.apawood.org

PRODUCT SUPPORT HELP DESK
 (253) 620-7400 ▪ E-mail Address: help@apawood.org

DISCLAIMER

APA Product Report® is a trademark of APA – The Engineered Wood Association, Tacoma, Washington. The information contained herein is based on the product evaluation in accordance with the references noted in this report. Neither APA, nor its members make any warranty, expressed or implied, or assume any legal liability or responsibility for the use, application of, and/or reference to opinions, findings, conclusions, or recommendations included in this report. Consult your local jurisdiction or design professional to assure compliance with code, construction, and performance requirements. Because APA has no control over quality of workmanship or the conditions under which engineered wood products are used, it cannot accept responsibility for product performance or designs as actually constructed.